

TECHNICAL SPECIFICATION

Insulating slabs made of ISOVER mineral wool. The production is based on defibring method of the minerals composition melt and additional additives and ingredients. The mineral fibres produced are processed into the final slab shape on the production line. The entire fibre surface is hydrophobic. The slabs in the construction should be protected suitably against the weather effects (outer cassette sheathing, diffusion and vapour-proof foil).

APPLICATION


ISOVER Uni slabs are suitable for unloaded insulations of the outer walls (ventilated facades under the cladding with insulant inserted into cassettes or frames), insulation of the pitch roofs, ceilings, false ceilings and other light sandwich constructions. The material is suitable for fire protection partition walls where the density $\geq 40 \text{ kg}\cdot\text{m}^{-3}$ is required.

PACKAGING, TRANSPORT, WAREHOUSING

ISOVER Uni insulation slabs are packed into the PE foil with package height up to 0,5 m. The slabs have to be transported in covered vehicles under conditions preventing their wetting or other degradation. The products are stored indoors or outdoors depending on the conditions specified in the current ISOVER price list.

BENEFITS

- fire-resistant
- very good thermal insulation performance
- excellent acoustic properties in terms of noise absorption
- low vapour resistance - good water vapour penetrability
- environmentally friendly and hygienic
- completely hydrophobic
- long life span
- resistant to wood-destroying pests, rodents, and insect
- easy workability - can be cut, drilled into, etc.
- dimensional stability during temperature change



DIMENSIONS AND PACKAGING

Thickness	[mm]	40	50	60	80	100	120	140	150	160	180	200
Length x width	[mm]	1200 x 600										
Volume per package	[pcs]	12	10	8	6	5	4	3	3	3	2	2
	[m ²]	8.64	7.20	5.76	4.32	3.60	2.88	2.16	2.16	2.16	1.44	1.44
Quantity per palette	[m ²]	0.35	0.36	0.35	0.35	0.36	0.35	0.30	0.33	0.35	0.26	0.29
	[m ²]	198.72	165.60	132.48	99.36	82.80	66.24	56.16	51.84	49.68	41.76	37.44
Declared thermal resistance R _b	[m ² ·K·W ⁻¹]	1.10	1.40	1.70	2.25	2.85	3.40	4.00	4.25	4.55	5.10	5.70

TECHNICAL PARAMETERS

Parameter	Unit	Methodology	Value	Designation code
Geometric shape				
Length <i>l</i>	[% , mm]	EN 822	±2 %	
Width <i>b</i>	[% , mm]	EN 822	±1.5 %	
Thickness <i>d</i>	[% , mm]	EN 823	-3 % or -3 mm ¹⁾ and +5 % or 5 mm ²⁾	Class of thickness tolerances T4
Deviation from squareness of the edge on length and width S _b	[mm·m ⁻¹]	EN 824	5	
Deviation from flatness S _{max}	[mm]	EN 825	6	
Relative change in length Δε _l , in width Δε _b , in thickness Δε _d	[%]	EN 1604	1	Dimensional stability under the specified temperature and humidity conditions DS (70,-)
Thermal technical properties				
Declared value of the thermal conductivity coefficient λ _b ³⁾	[W·m ⁻¹ ·K ⁻¹]	Declaration according to EN 13162+A1 Measurement according to EN 12667	0.035	
Design thermal conductivity λ _b ⁴⁾	[W·m ⁻¹ ·K ⁻¹]	ČSN 73 0540-3	0.038	
Specific heat capacity c _d	[J·kg ⁻¹ ·K ⁻¹]	ČSN 73 0540-3	800	
Fire safety properties				
Reaction to fire class	[-]	Declaration according to EN 13501-1+A1	A1	
Maximum temperature for use	[°C]		200	
Melting temperature t _f	[°C]	DIN 4102 part 17	≥ 1000	
Hydrothermal properties				
Water vapour diffusion resistance factor μ	[-]	EN 13162+A1	1	Declared value for water vapour diffusion resistance factor MU1
Other properties				
Density	[kg·m ⁻³]	EN 1602	40	

¹⁾ Whichever gives the greatest numerical tolerance.

²⁾ Whichever gives the smallest numerical tolerance.

³⁾ Declared values were set under the following conditions (reference temperature 10 °C, humidity u_{dry}, which is reached by drying) according EN ISO 10456.

⁴⁾ It is valid for typical use in construction with risk of condensation. In the case of construction without any risk of condensation it is possible to use the declared value of thermal conductivity.

RELATED DOCUMENTS

- Declaration of Performance CZ0001-005
- Environmental Product Declaration
- ISO 9001, ISO 14001, ISO 45001, ISO 50001

TECHNICAL PARAMETERS

Parameter	Unit	Methodology	Value	Designation code							
Acoustic properties⁵⁾											
The practical sound absorption coefficient α_p	[-]	EN 13162+A1	Level of practical sound absorption coefficient	AP							
		EN ISO 11654									
		Measurement according to EN ISO 354									
	Frequency	125 Hz	250 Hz	500 Hz	1000 Hz	2000 Hz	4000 Hz				
	Thickness	40 mm	60 mm	80 mm	100 mm						
		0.15	0.25	0.35	0.45	1.00	1.00	1.00	1.00	1.00	1.00
Weighted sound absorption coefficient α_w Sound Absorption Average α_{sfr} Noise Reduction Coefficient NRC	[-]	EN ISO 11654 (for NRC according to ASTM C423)	Level of weighted sound absorption coefficient				AW				
		Single number value	α_w		α_{sfr}		NCR				
	Thickness	40 mm	0.70 (MH)		0.79		0.80				
		60 mm	1.00		0.93		0.95				
		80 mm	1.00		1.01		1.00				
100 mm	1.00		1.05		1.05						
Specific air flow resistivity r	[kPa·s·m ⁻²]	EN 13162+A1	Level of air flow resistivity			AFr					
		Measurement according to EN ISO 9053-1	12,3								
Environmental properties / impacts											
Volume of Pre-consumer recycled content for production⁵⁾	[%]	ČSN ISO 14021	72								
Volume of Post-consumer recycled content for production⁵⁾	[%]	ČSN ISO 14021	0								
Non-hazardous waste disposed⁶⁾	[kg /FU ⁷⁾]	EN 15804+A1, ČSN ISO 14025	0.946	NHWD							
Total use of non-renewable primary energy resources	[MJ /FU]	EN 15804+A1, ČSN ISO 14025	49	PENRT							
Global Warming Potential	[kg CO ₂ ekv. /FU]	EN 15804+A1, ČSN ISO 14025	4.97	GWP							
Ozone Depletion	[kg CFC 11 ekv. /FU]	EN 15804+A1, ČSN ISO 14025	2.72 E-07	ODP							
Acidification potential	[kg SO ₂ ekv. /FU]	EN 15804+A1, ČSN ISO 14025	0.0361	AP							
Eutrophication potential	[kg PO ₄ ³⁻ ekv. /FU]	EN 15804+A1, ČSN ISO 14025	0.00356	EP							
Photochemical ozone creation	[kg C ₂ H ₄ ekv. /FU]	EN 15804+A1, ČSN ISO 14025	0.00471	POPC							
Abiotic depletion potential for non-fossil resources	[kg Sb ekv. /FU]	EN 15804+A1, ČSN ISO 14025	6.73 E-07	ADP-elements							
Abiotic depletion potential for fossil resources	[MJ (Calorific value) /FU]	EN 15804+A1, ČSN ISO 14025	45.9	ADP-fossil fuels							

⁵⁾ According to ČSN EN ISO 14021 part 7.8 Recycled content.

⁶⁾ In this case it is standard mixed waste.

⁷⁾ FU = functional unit (1 m² of insulation by 100 mm thick for live cycle phases A1-A3).



Example of product application ISOVER Uni